

### Product Datasheet: ARC MX2

# 100% solids, ceramic reinforced, multi-component system, formulated for extreme sliding-wear and abrasion caused by fine particles. ARC MX2 industrial coating is designed to:

- Protect surfaces against both dry fine particle erosion and wet slurry abrasion
- Restore worn equipment to near original condition
- Provide a longer lasting alternative to rubber linings and ceramic wear tiles
- Resist a broad pH spectrum
- Easily apply by trowel

#### **Application Areas**

- Cyclones
- Valves
- Hopper bins
- Pulp dewatering screws
- Wear plates
- Slurry pumps
- Agitators
- Mixers

- Cleaner cones
- Pipe spools
- Pipe elbows
- Pulverizers

## Packaging and Coverage Nominal, based on a 3 mm (120 mil) thickness 2.5 liter kit covers 0.83 m² (8.97 ft²)

- 2.3 mer kit covers 0.03 m (0.37 m
- 16 liter kit covers 5.33 m² (57.41 ft²)

Note: Components are pre-measured & pre-weighed. Each kit includes mixing and application instructions. 2.5 liter kit includes tools.

Color: White





#### **Features and Benefits**

- Tough, ceramic reinforced coating resists broad range of slurries
  - Extends life of equipment exposed to fine particle wear
- 100% solids; no VOCs; no free isocyanates
  - Enhances safe use
  - Bonds easily to prepared surfaces
  - Serves demanding applications
- Low viscosity formulation
  - Simplifies application
  - Lowers installed cost
  - Easily molded

Technical Data			
Composition Matrix	A modified epoxy resin reacted with an aliphatic amine curing agent		
Reinforcement (Proprietary)	Blend of medium and fine particle size, high purity ${\rm Al_2O_3}$ ceramic beads and powders, pretreated with polymeric coupling agent		
Cured Density		2.4 g/cc	150 lb/ cu.ft.
Compressive Strength	(ASTM D 695)	920 kg/cm <sup>2</sup>	13,100 psi
Flexural Strength	(ASTM D 790)	530 kg/cm <sup>2</sup>	7,500 psi
Pull-Off Adhesion	(ASTM D 4541)	238.9 kg/cm <sup>2</sup> (23.5 MPa)	3,400 psi
Tensile Strength	(ASTM D 638)	290 kg/cm <sup>2</sup>	4,100 psi
Impact Resistance (Reverse)	(ASTM D 2794)	7.9 N-m	70 in-lbs.
Shore D Durometer Hardness	(ASTM D 2240)	90	
Vertical Sag Resistance, at 21°C (70°F) and 6 mm (240 mil)		No Sag	
Maximum Temperature (Dependent on service)	Wet Service Dry Service	95°C 205°C	203°F 400°F
Shelf life (unopened containers)	2 years [stored between 10°C (50°F) and 32°C (90°F) in dry, covered facility]		



A.W. Chesterton Company
860 Salem Street, Groveland, MA 01834 USA
Tel +1 978-469-6888 Toll Free 844-469-6888
www.arc-epc.com ARCInfo@Chesterton.com
© 2016 A.W. Chesterton Company

Registered trademark owned and licensed by A.W.
 Chesterton Company in USA and other countries,
 unless otherwise noted.

Technical Data reflect results of laboratory tests and are intended to indicate general characteristics only. Since many actual application circumstances are beyond Chesterton's knowledge and/or control, the product user must determine the suitability of the products it intends to use for its particular purpose and assume all risks and liabilities in connection therewith. CHESTERTON DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.